



Biglie d'allumina per macinazione - Allumina balls for grinding : KT 100 EXTRA

Biglie allumina per compressione , alta qualità ed alta resistenza all'usura
Allumina balls produced by compression , high quality and high abrasion resistance

Analisi Chimica / Chemical Analysis

Al₂O₃ > 92,00 %

Bulk Density : 3,62 gr/cm³

Mohs hardness : 9

Water absorption : 0%

Colour : White

Standard dimensions :

mm1 ; 3-5 ; 5-7 ; 7-9 ; 9-11 ; 13 : 15 ; 18 ; 20 ; 22 ; 25 ; 30 ; 40 ; 45 ; 50 ; 60 ; 70

Imballaggio / packaging :

saccone 1000/500kg su paletta , bigbag 1000kg/500kg on wooden pallet

sacco 25kg su paletta , 25kg bag on wooden pallet



BAAN Industrial Raw Materials

Via Maestri del Lavoro n°10 – 41043 Colombaro di Formigine - Italia

Cell: +39.335.7740438 – Tel/Fax: +39.059.553.283

email: info@baanmaterials.com ; web site : www.baanmaterials.com